



***Mina***

# Iron Copper

## Neolith / Neolith

PROCEDENCE / PROCEDENCIA  
FINISHED / ACABADOS  
FORMATS / FORMATOS

APPLICATIONS / APLICACIONES

Spain / España

Polished, Rough and Honed / Pulido, Bruto y Apomazado

Slabs and Tiles / Tabla y Losa

2 cm - 60 x 60 x 1" - 60 x 60 x 1,5" - 60 x 60 x 2" - 61 x 30 x 1"

90 x 90 - 120 x 120 - 305 x 305 x 1" - 457 x 457 x 1,5"

Interiors and Exteriors / Interiores y Exteriores

Specially suitable for kitchen and bathroom countertops /

Especialmente indicado para encimeras de cocina y baño

Apparent density	kg/m <sup>3</sup>	2670 +/- 10
Open Porosity	%	0,9 +/- 0,1
Flexural Strength		
	Mean Value	MPa 11,20
	Standar Deviation	MPa 2,10
	Low Expected Value	MPa 7,20
Decrease of flexural strength after 48 cycles frost-taw	%	11,00
Water absorption to atmospheric pressure	%	0,34 +/- 0,02
Water absorption by capillarity	g/m <sup>2</sup> s	0,73 +/- 0,31
Permeability to the water steam	u	200 / 250
Abrasion Resistance	mm	19,50 +/- 0,50
Fire Resistance		A1